

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
30 June 2005 (30.06.2005)

PCT

(10) International Publication Number
WO 2005/058488 A3

(51) International Patent Classification⁷: **B01J 23/10**,
29/06, 37/04, C10G 11/04, 11/05, 45/04, B01J 23/06,
23/24

(21) International Application Number:
PCT/EP2004/013913

(22) International Filing Date: 6 December 2004 (06.12.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/527,756 9 December 2003 (09.12.2003) US
04075063.0 9 January 2004 (09.01.2004) EP

(71) Applicant (for all designated States except US): **AKZO
NOBEL N.V.** [NL/NL]; Velperweg 76, NL-6824 BM Ar-
nhem (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **JONES, William**
[GB/GB]; 56, Lantree Crescent, Cambridge CB2 2NJ
(GB). **STAMIREES, Dennis** [US/US]; 3401 Colony Plaza,
Newport Beach, CA 92660 (US). **O'CONNOR, Paul**
[NL/NL]; Hogebrinkerweg 9, NL-3871 KM Hoevelaken
(NL). **BRADY, Michael** [US/US]; 4248 Rhodes Avenue,
Studio City, CA 91604 (US).

(74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel
N.V., Intellectual Property Department (Dept. AIP), P.O.
Box 9300, NL-6800 SB Arnhem (NL).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
25 August 2005

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE PREPARATION OF AN OXIDIC CATALYST COMPOSITION COMPRISING A DIVALENT
AND A TRIVALENT METAL

(57) Abstract: Process for the preparation of an oxidic catalyst composition consisting of one or more trivalent metals preferably
aluminum, one or more divalent metals preferably magnesium and more than 18 wt% of one or more compounds selected from
the group consisting of rare earth metal compounds, phosphorus compounds, and transition metal compounds, which process com-
prises the steps of preparing a precursor mixture consisting of (i) one or more trivalent metal compounds, (ii) one or more divalent metal
compounds, (iii) one or more compounds selected from the group consisting of rare earth metal compounds, and transition metal
compounds, and (iv) optionally water, which precursor mixture is not a solution. The resulting oxidic catalyst composition is suitable
as a metal trap and SO_x sorbent FCC processes.



WO 2005/058488 A3